

# MULTICLAD Roof and Wall




MultiClad is an economical roof and wall cladding and is suitable for warehouse roof and walls. It has good water carrying capacity at low pitches.

MultiClad is available in a wide range of colours and also suitable for domestic applications.

## Product Details

### Profile



## Material Specification

0.42 or 0.48	Zincalume®	G550 AM125
0.42 or 0.48	Galvanised	G550 Z450
0.42 or 0.48	Colorbond®	G550 AM100

### Special Orders


Stainless Steel, Metallic, Coolmax and Ultra

## Product Mass

BMT		kg/m <sup>2</sup>
0.42	Zincalume®	4.24
0.42	Colorbond®	4.27
0.42	Galvanised	4.65
0.48	Zincalume®	4.81
0.48	Colorbond®	4.85
0.48	Galvanised	5.23

## Wind Load Conversion


Wind Classification	Region & Category
(Domestic)	(Commercial/Industrial)
N1 (W28)	Reg A, Cat 3
N2 (W33)	Reg A, Cat 2.5 - Reg B, Cat 3
N3 (W41)	Reg A, Cat 2 - Reg B, Cat 2.5
N4 (W50)	Reg B, Cat 2



## Maximum Support Spacings (mm)

Type of Span	Thickness (mm)	BMT
	.42	.48
<b>ROOFS</b>		
Single Span	1100	1600
End Span	1300	1800
InternalSpan	1900	2600
Unstiffened Eaves Overhang	150	200
<b>WALLS</b>		
Single Span	2100	2400
End Span	2700	2700
InternalSpan	2700	2700
Overhang	200	200

Maximum Support Spacing has been determined by load tests and deflection in accordance with AS 1562-1 AS 4040 1&2 1992.



# MultiClad - Roof and Wall



## .42 Bmt MultiClad Roof & Wall

### Limit State Wind Pressure Capacities (kpa)

4 Screw intermediate 4 Screw Gutter & Apex Line				Walls Only						
SPAN TYPE		Span mm								
		900	1100	1300	1500	1800	1900	2100	2400	2700
SINGLE	Serviceability	3.90	3.10	2.40	1.85	1.25	1.10	0.75		
	Strength	8.00	7.00	6.10	5.15	3.75	3.25	2.30		
END	Serviceability	3.60	3.20	2.80	2.50	1.95	1.80	1.60	1.20	0.80
	Strength	6.00	5.55	5.10	4.65	4.05	3.80	3.04	2.70	2.10
INTERNAL	Serviceability	4.20	3.80	3.35	2.90	2.35	2.20	1.90	1.50	1.20
	Strength	8.00	7.00	6.10	5.35	4.40	4.10	3.70	3.25	3.00

## .48 Bmt MultiClad Roof & Wall

### Limit State Wind Pressure Capacities (kpa)

4 Screw intermediate 4 Screw Gutter & Apex Line				Walls Only						
SPAN TYPE		Span mm								
		900	1200	1500	1600	1800	2100	2400	2600	2700
SINGLE	Serviceability	5.00	3.05	1.80	1.63	1.15	0.75	0.60		
	Strength	10.00	8.55	7.00	6.50	5.45	3.95	2.60	1.55	1.10
END	Serviceability	5.10	3.85	2.85	2.55	2.12	1.55	1.20	0.95	0.85
	Strength	8.60	6.70	5.20	4.80	4.20	3.55	3.00	2.70	2.65
INTERNAL	Serviceability	5.96	4.85	3.85	3.55	3.15	2.40	1.95	1.72	1.62
	Strength	9.00	8.00	7.00	6.65	5.45	5.25	4.40	4.00	3.80

Fixing to steel 1.0 minimum thickness.

### Compliance

Wind pressure capacity tables have been determined by full scale testing in accordance with AS 1562.1 and AS 4040.1&2 1992.

Non-Cyclonic areas.

The pressure considered is based on buildings up to 10m high in Region B, Terrain Category 3,  $M_3=0.85$ ,  $M_1=1.0$ ,  $M=1.0$  with the following assumptions made:

#### Roofs

$C_{pi} = +0.20$ ,  $C_{pe} = -0.90$ ,  $K_1 = 2.0$  for single and end spans,  $K_1 = 1.5$  for internal spans.

#### Walls

$C_{pi} = +0.20$ ,  $C_{pe} = -0.65$ ,  $K_1 = 2.0$  for single spans,  $K_1 = 1.5$  for internal spans.



Roof Pressure Test




# MultiClad - Roof and Wall



## Fixing Details


### Crest: 4 Fasteners




### Valley: 4 Fasteners



### Crest Fix Roof and Walls



### Valley Fix Walls only



## MultiClad Roofing

Should be laid square to the gutter line and into the prevailing wind. The sheet is fastened at every rib. Sheets must be turned up at the apex and down at the gutter line. Side lap fastener is recommended mid span when span exceeds 1200mm.

## MultiClad Wall

MultiClad is very popular for warehouse walls and farm sheds. It is easily installed and has good spanning capability. Side lap fastener is recommended mid span when the span exceeds 1200mm.

## Design Considerations

The recommended minimum pitch is 2 degrees. For long run roofing the pitch should be increased and spans considered.

### Length

- MultiClad is custom cut to your exact length.
- The maximum length for pierce fixed roofing is 23.7m before an expansion joint is required. This length is recommended for light colours only. Dark colours should not exceed 16.0m because of increased thermal expansion.

### Foot Traffic

- Always walk over purlins and place your foot print in the pan only. To avoid sheet damage don't stand on ribs.


### Handling On Site

- Delivery to site to be the responsibility of the customer.
- Sheets should be kept dry and clear of the ground.
- When handling sheets use dry, clean gloves and don't drag sheets over each other.

### Cutting

- It is recommended to cut sheets with tin snips or a nibbler. Don't use an abrasive disc cutter.

## Expansion Joint



## Fasteners

	Fixing to Steel	Fixing to Timber
Crest Fixing Roof	12 - 14 Tekes or M6 x 50mm Tekes	12 Type 17
Neo Washer	.55-1.0mm Thick Steel	M6 Tekes
Walls Neo Washer	10 - 16 x 16 Tekes	12 x 25 Type 17

